



Dansk Træemballage A/S  
 Att. Gert Fuglkjær  
 Stampemøllevej 8  
 6760 Ribe

Navervej 1  
 DK-6600 Vejlen

## ANALYTICAL REPORT

Our ref.: Vibeke Schøler  
 Direct phone.: 4262 7696  
 analyselab-vest@force.dk

## Analyses of Solid Biofuels

Journal no.: W24-60  
 Report date: 25.01.2024

Sample mark: Dansk Træemballage Stampemøllen Januar 2024  
 Description: -Wood Pellets-  
 Sample size: 15,0 kg  
 Received: 15.01.2024  
 Analysed: 15.01.2024 - 24.01.2024  
 Sample preparation: According to DS/EN 14780 (2017)

Parameter	Method	Unit	Results		
			as received	dry basis	dry, ashfree
Total Moisture	DS/EN ISO 18134-1 (2015)	%	8,0 ± 0,3		
Ash *	DS/EN ISO 18122 (2015)	%	0,34	0,37	
Net Calorific Value *	Calculated on received sample <sup>1)</sup>	MJ/kg	17,2	18,9	19
		Mcal/kg	4,1		
Average diameter *	DS/EN ISO 17829 (2015)	mm	6,0		
		Standard deviation	mm	0,0	
Average length *	DS/EN ISO 17829 (2015)	mm	15,0		
		Standard deviation	mm	5,3	
Durability mechanical	DS/EN ISO 17831-1 (2015)	%	99,1		
Particles < 3,15 mm *	DS/EN ISO 17831-1 (2015)	%	0,1		
Bulk density *	DS/EN ISO 17828 (2015)	kg/m <sup>3</sup>	660		
Ash Fusibility	CEN/TS 15370-1 (2006)	Unit	In dry ash prepared at 550 °C		
Deformation temperature		°C	1450	- repeatability 30	
Hemisphere temperature		°C	>1480	- repeatability 30	
Flow temperature		°C	>1480	- repeatability 30	

The reported expanded uncertainty provides a level of confidence of app. 95 %

<sup>1)</sup> Net Calorific Value is calculated from the measured content of moisture and ash, as well as an experienced value base of 19 MJ/kg for the net calorific value of wood pellets on the combustible substance (dry- and ashfree base).

The majority of biofuels analyzed have a net calorific value, on dry- and ashfree base, between 18,5-19,5 MJ/kg.

\* Not included in this accreditation.

  
 Jesper Hinz  
 Specialist